

# Heat Treatment Effect on the Hardness of Aluminium LM13 – MgO Particulate Composite

C S Ravindra Sagar<sup>1</sup>, T K Chandrashekar<sup>2</sup> Batluri Tilak Chandra<sup>3</sup>

Research scholar<sup>1,3</sup> and Professor<sup>2</sup>,

Department of Mechanical Engineering,

Sri Siddhartha Institute of Technology,

Tumkur-572105, Karnataka, India.

Department of Mechanical Engineering,

Mangalore Institute of Technology,

Moodabidre, Mangalore- 574225, Karnataka, India

---

## ABSTRACT

*Ceramic reinforced Aluminum matrix composite materials are increasing wide acknowledgment in the designing application. Incorporation of MgO as reinforcement in aluminium LM13 Composite enhances its hardness. In the present examination aluminium LM13/MgO composites were produced by vortex strategy by shifting the weight level of MgO particulates from 0wt% to 10wt% in the means of 2wt%. The As-cast and its composites have been subjected to solutionizing treatment at a temperature of 530° C for 2 hours, trailed by extinguishing in various medians, for example, air, water and ice. The extinguished hardness examples were subjected to artificial aging at 164° C. Microstructural behaviour were completed to comprehend nature of structure. The hardness test was led on both aluminium LM13 and aluminium LM13/MgO particulate composite, when warm treatment. Aluminium LM13/MgO particulate composites displayed critical change in hardness when contrasted and aluminium LM13.*

**Key Words:** LM13, MgO, Solutionizing, Artificial Ageing, Hardness.

---

## 1. INTRODUCTION

MMC's are increasing wide prominence in a few segments because of its enhanced mechanical properties. When contrasted with metals, especially when weight is considered as major factor. Aluminum composites are used in different applications few of them are Pistons, brake plate and cylinder and so on [1]. Aluminum composite increases the particulate reinforcement increases the strength by following traditional methods [2, 3]. SiC is most normal molecule utilized in aluminum alloy composites [4, 5] for light weight applications by addition of clay particles in the matrix the strength of the composite increases [6] Al6061 combination is warm treatable and subsequently additionally increment in quality can be normal [7], heat treatment process improves the strength and fit to design the material for industries [8]. Aluminum LM13 compound have various advantages like formability weldability, consumption protection and ease. For generation of Aluminum particulate strengthened composite blend throwing technique gives off an impression of being promising strategy among different regular handling strategies. Warmth Treatment procedure to alter the microstructure of aluminum compound composites with aluminum is the last generation phases of composite [9]. A large portion of the scientists have explored aluminum composites utilizing SiC, Al<sub>2</sub>O<sub>3</sub>, MgO, Zircon and so forth., and these composites are industrially accessible in various basic structures [10]. In the present work the maturing conduct of LM13/MgO composites containing MgO particulates is contrasted and warm treated LM13 combination were contemplated.

## 2. EXPERIMENTAL PROCEDURE

### 2.1 Development of Composites

Aluminium LM13 as matrix and MgO as reinforcement the chemical composition are as shown in Tables 1.

Table1.1. Chemical Composition of LM13 alloy

Si	Mg	Cu	Fe	Ti	Cr	Ni	Mn	Al
12.1	1.2	0.8	0.8	0.02	0.07	0.9	0.2	Bal.

Magnesium oxide used as a reinforcement material. It is white fine powder form & hygroscopic in nature.

Table 1.2: Chemical composition of reinforcement MgO

Appearance	White Powder
Solubility	Partly soluble in water
Molecular formula	MgO
Molecular weight	40.30
Density	3.70 g/cc
Melting Point	2800°C

In this investigation the matrix Al LM13 addition of particulates MgO with different wt.% (2 wt.% to 10 wt.% in steps of 2). In stir casting process the development of LM13 is heated to a temperature of 700° C to 800° C in a graphite crucible, then particulates MgO is pre heated to the temperature of 400° C and thoroughly stirred at a speed of 550 rpm at duration of 10 to 15 min. The ready mixed composite is poured to a pre heated cast iron die till it solidifies. The unreinforced and reinforced composite are studied for microstructure analysis and hardness test.

### 2.2 Heat Treatment

The obtained material is solutionized at 530° C for a period of 2 hours in muffle furnace and quenched in different mediums like air, water and ice and followed by artificial ageing at 164° C at duration 2 to 10 hours in step of 2 hours.

### 2.3 Hardness Test

The Brinell hardness tests were done according to ASTM-E10-95 standard. The specimen diameter is 20 mm, the testing specimens is cleaned in various emery papers and the tests were conducted in 3 distinct areas on the hardness round specimens both for as cast and heat treated Al LM13/MgO composite material.

## 3. RESULTS AND DISCUSSION

### 3.1 Microstructure analysis




Figure3.1 Micrograph of Al (LM13)/0wt% of MgO




Figure3.2 Micrograph of Al (LM13)/ 2wt% of MgO




Figure3.3 Micrograph of Al (LM13)/ 4wt% of MgO




Figure3.4 Micrograph of Al (LM13)/ 6wt% of MgO

The specimen for the minute inspection was set up by metallographic methodology scratched in Keller's specialist, analysed under optical magnifying instrument. The micrographs plan show the confirmation of negligible porosity in both aluminium LM13 and its aluminium LM13 - MgO particulate composites. Micrograph demonstrates the almost uniform dissemination of the particles in the composite.

### 3.2 Hardness






Figure 3.5 Variation of hardness with increase in wt% of reinforcement for aluminium LM13-MgO particulate composites

In the figure 3.5 shows that the increase in the weight percentage of MgO particulate it is found that significant improvement in hardness, it is due to presence of hard ceramic MgO particulate improves the hardness and wear resistance of Al LM13/MgO composite material [11-15].




**Figure 3.6 Variation of hardness with increase in ageing for aluminium LM13 matrix alloy and its aluminium LM13-MgO particulate composites for Air quenched under different heat treat conditions**

Figure 3.6 shows that on solutionized with air quenching for period of 6 hrs. The aluminium LM13/MgO at 6wt% indicated most noteworthy change in hardness around 33%.



**Figure 3.7 Variation of hardness with increase in ageing for aluminium LM13 matrix alloy and its aluminium LM13-MgO particulate composites for water quenched under different heat treat conditions**

Figure 3.7 shows that on water quenching for 6 hrs. The aluminium LM13/MgO at 6wt% demonstrated most extraordinary change hardness around 35%.



**Figure 3.8 Variation of hardness with increase in ageing for aluminium LM13 matrix alloy and its aluminium LM13-MgO particulate composites for Ice quenched under different heat treat conditions**

Figure 3.8 shows that on Ice quenching for 6hrs the aluminium LM13/MgO at 6wt% demonstrated most prominent difference in hardness of around 38%. Considering all three medians Air, Water and Ice the percentage shows that ice Quenching obtains maximum hardness.

#### 4. CONCLUSIONS

1. Aluminium LM13 composites have been effectively created with genuinely uniform scattering of MgO particles utilizing vortex strategy.
2. The microstructural examine unmistakably uncovers the about uniform circulation of support particulates in the Aluminium LM13.
3. The hardness of the composites expanded altogether with expanded substance of MgO particles. Warmth treatment significantly affects Brinell hardness of Aluminium LM13 alloy and its composites. Ice extinguishing took after by simulated maturing for 6 hrs. brought about greatest hardness of matrix alloy and its composites.

## REFERENCES

- [1] R. Anwar khan, C. S Ramesh and A. Ramachandra, "Heat treatment of Al6061-sic composites" Proceedings of international companies on manufacturing (Dhaka ICM) pp21-28, 2002.
- [2] K. Mahadevan, K. Raghukandan, A. Venkataraman, B.C. Pai, U.T.S. Pillai. 2003. Mater. Sci. Forum. 437/438, 223-226.
- [3] K. Mahadevan, K. Raghukandan, A. Venkataraman, B.C. Pai, U.T.S. Pillai. 2005. Studies on the effect of delayed aging on the mechanical behaviour of AA 6061 SiCp composites. Material Science and Engineering. 396: 188-193.
- [4] K. Raghukandan, K. Hotamoto, J.S. Lee, A. Chiba, B.C. Pai. 2003. J. Mater. Sci. Tech. 19(4): 341-345.
- [5] J. Hasim, L. Looney, M.S.J. Hasmi. J. Mater. Proc. Tech. 92/93, 1-7.
- [6] V.K. Lindroos, M.J. Talvitie. 1995. J. Mater. Proc. Tech. 53: 273-284.
- [7] M.Gupta, and M.K.Surappa, "Effect of wt% of SiC particulates on the ageing behavior of Al6061/SiC MMC's", Journal of Material Science, 14(1995), 1283-1285.
- [8] Rajan.T.V, Sharma C.P, Ashok Sharma, 1998, Heat treatment principles Techniques, Rajkamal Electric Press, India, Page 142-149.
- [9] M.K. Surappa, PhD Thesis. Indian Institute of Sciences, Bangalore, India, 1979.
- [10] J.P. Pathak, J.K. Singh and S. Mohan. 2006. Synthesis and characterization of Aluminium-Silicon-Silicon carbide composite. Indian Journal of Engineering & Material Sciences. Vol. 13, June. pp. 238-246.
- [11] Pai, B. C., Ray, S., Prabhakar, K. V. and Rohatgi, P. K. Fabrication of aluminium alumina (magnesia) particulate composites in foundries using magnesium additions to the melts. Mater. Sci. Engng, 1976,24,31.
- [12] Sato, A. and Mehrabian, R. Aluminium matrix composites: fabrication and properties. Metall. Trans. B, 1976, 7, 443.
- [13] S C Sharma, S pual vizhian, A Shashishankar, M Krishna "Influence of heat treatment on microstructural and tensile properties of Aluminium E-Glass short fiber composites" Journal of Mechanical Behaviours of materials, volume 14, issue 4- 5, April 2011.
- [14] D Ramesh, R. P Swamy and T.K Chandrashekar." ARPN Journal of Engineering and Applied science" ISSN 1819 - 6608. Effect of weight percentage on Mechanical properties of frit particulate reinforced Al6061 composite Vol.5, No.1, January 2010.
- [15] Arun kumar M. B and R. P swamy, "Evaluation of Mechanical properties of Al6061, fly ash and E-glass fiber reinforced Hybrid metal matrix composites", ARPN Journal of Engineering and Applied science, Vol. 6, No. 5, May 2011.